

DMH 307 NBR 73

Mechanical, Physical and Thermal Properties

Nitrile butadiene rubber

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour				black		black
hardness	23°C/3 sek.	ISO 868	Shore A	75 ± 5	Shore A	75 ± 5
hardness	23°C/15 sek.	ISO 868	Shore A	71 ± 5	Shore A	71 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 7	psi	≥ 1015
tensile strength	23°C	DIN 53 504	MPa	≥ 16	psi	≥ 2320
elongation at break	23°C	DIN 53 504	%	≥ 190	%	≥ 190
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 5	lbf/inch	≥ 28
spec. gravity	23°C	ISO 1183	kg/m ³	1230	g/cm ³	1,23
rebound elasticity	23°C	DIN 53 512	%	28	%	28
abrasion	23°C	DIN 53 516	mm ³	132	mm ³	132
compression set	*	ISO 815	%	≤ 5	%	≤ 5
compression set	**	ISO 815	%	≤ 8	%	≤ 8
compression set	***	ISO 815	%		%	
minimum service temperature			°C	-30	°F	-22
maximum service temperature			°C	90	°F	194
temp. max water/steam			°C		°F	
temp. max hot air			°C		°F	

* 24h 70°C 25% def. ** 24h 100°C 25% def. *** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on butadiene and acrylonitrile

Resistant to: oil, petrol and crude oil

Not resistant to: conc. acids, conc. lyes and polar solvents

revision: 03-2024

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH Dichtungs- und Maschinenhandel GmbH

Industriepark West 11
8772 Traboch
Austria
dmh.at

p. +43 (0)3833/200 60-0
f. +43 (0)3833/200 60-500
e. office@dmh.at

