

# DMH 333 EPDM FDA black

Mechanical, Physical and Thermal Properties

Ethylene propylene diene rubber

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour				black		black
hardness	23°C/3 sek.	ISO 868	Shore A	85 ± 5	Shore A	85 ± 5
hardness	23°C/15 sek	ISO 868	Shore A	84 ± 5	Shore A	84 ± 5
modulus 100%	23°C	DIN 53 504	MPa		psi	
tensile strength	23°C	DIN 53 504	MPa	≥ 10	psi	≥ 1450
elongation at break	23°C	DIN 53 504	%	≥ 100	%	≥ 100
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 4	lbf/inch	≥ 23
spec. gravity	23°C	ISO 1183	kg/m <sup>3</sup>	1190	g/cm <sup>3</sup>	1,19
rebound elasticity	23°C	DIN 53 512	%	40	%	40
abrasion	23°C	DIN 53 516	mm <sup>3</sup>	195	mm <sup>3</sup>	195
compression set	*	ISO 815	%	≤ 10	%	≤ 10
compression set	**	ISO 815	%	≤ 10	%	≤ 10
compression set		ISO 815	%		%	
minimum service temperature			°C	-45	°F	-49
maximum service temperature			°C	130	°F	266
temp. max water/steam			°C	130	°F	266
temp. max hot air			°C	150	°F	302

\* 24h 70°C 25% def. \*\* 24h 100°C 25% def. \*\*\* 24h 150°C 25% def.

## Chemical Properties

Copolymer, based on ethylene, propylene and diene

Resistant to: (hot) water, acids, bases, ketones, HFC- and HFD-fluids, lyes, brake fluids based on polyglycols

Not resistant to: aliphatic, aromatic and chlorinated hydrocarbons, greases, fuels

<b>Foodstuff approval</b>	FDA compliant, 1935/2004 EC Maximum recommended service temperature (FDA applications): 90°C
revision: 03-2024	

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

## DMH Dichtungs- und Maschinenhandel GmbH

Industriepark West 11  
8772 Traboch  
Austria  
[dmh.at](http://dmh.at)

p. +43 (0)3833/200 60-0  
f. +43 (0)3833/200 60-500  
e. [office@dmh.at](mailto:office@dmh.at)

