

# DMH 353 FPM ED

Mechanical, Physical and Thermal Properties

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour				black		black
hardness	23°C/3 sek.	ISO 868	Shore A	85 ± 5	Shore A	85 ± 5
hardness	23°C/15 sek	ISO 868	Shore A	83 ± 5	Shore A	83 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 6	psi	≥ 870
tensile strength	23°C	DIN 53 504	MPa	≥ 10	psi	≥ 1450
elongation at break	23°C	DIN 53 504	%	≥ 190	%	≥ 190
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 20	lbf/inch	≥ 114
spec. gravity	23°C	ISO 1183	kg/m <sup>3</sup>	1860	g/cm <sup>3</sup>	1,86
rebound elasticity	23°C	DIN 53 512	%	11	%	11
abrasion	23°C	DIN 53 516	mm <sup>3</sup>	175	mm <sup>3</sup>	175
compression set	*	ISO 815	%	≤ 30	%	≤ 30
compression set	**	ISO 815	%	≤ 35	%	≤ 35
compression set	***	ISO 815	%	≤ 45	%	≤ 45
minimum service temperature			°C	-20	°F	-4
maximum service temperature			°C	220	°F	428
temp. max water/steam			°C		°F	
temp. max hot air			°C	300	°F	572

\* 24h 70°C 25% def. \*\* 24h 100°C 25% def. \*\*\* 24h 150°C 25% def.

## Chemical Properties

Ter-polymer, based on fluorine

Resistant to: fats, crude oil, mineral oil, gasoline, aliphatic and aromatic hydrocarbons

Not resistant to: glycols, ketones, most fluids containing amines, water/steam

revision: 03-2024

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

## DMH Dichtungs- und Maschinenhandel GmbH

Industriepark West 11  
8772 Traboch  
Austria  
[dmh.at](http://dmh.at)

p. +43 (0)3833/200 60-0  
f. +43 (0)3833/200 60-500  
e. [office@dmh.at](mailto:office@dmh.at)

