

DMH 661 PTFE LF

Mechanical, Physical and Thermal Properties

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour				grey		grey
density/specific gravity	23 °C	DIN 53479	kg/m ³	2090	g/cm ³	2,09
hardness	23 °C/3 sek.	ISO 868	Shore D	57 ±3	Shore D	57 ±3
hardness	23°C/15 sek.	ISO 868	Shore D	56 ±3	Shore D	56 ±3
ball indentation hardness	23 °C	DIN 53456 H 135/30	MPa		psi	
tensile strength	23 °C	ASTM D 4745-11a	MPa	≥ 20	psi	≥ 2900
elongation at break	23 °C	ASTM D 4745-11a	%	≥ 320	%	≥ 320
compressive strength	23 °C	DIN 53455	MPa		psi	
thermal conductivity		DIN 52612	$\frac{J * 10^3}{m * h * K}$		$\frac{J * 10^3}{m * h * K}$	
coefficient of thermal expansion	25 °C - 200 °C		K ⁻¹ * 10 ⁻⁵		K ⁻¹ * 10 ⁻⁵	
coefficient of friction *	23 °C		μ		μ	
minimum service temperature			°C	-200	°F	-328
maximum service temperature			°C	260	°F	500
young's modulus	23 °C	DIN 53457	MPa		psi	

* coefficient of friction dry dynamic Steel 16MnCr5 v=0,6m/s; p=0,05 MPa; t=5h

Chemical Properties

Resistant to almost all chemicals

Not resistant to halogenides, elemental fluorine, CF₃, molten alkali metals

revision: 03-2024

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH Dichtungs- und Maschinenhandel GmbH

Industriepark West 11
8772 Traboch
Austria
dmh.at

p. +43 (0)3833/200 60-0
f. +43 (0)3833/200 60-500
e. office@dmh.at

